

# Connect 8.

## Technical data.

BERRY  ALLOC

11/2023

	contains	m <sup>2</sup>	ft <sup>2</sup>	weight
1 pack Connect 8	9 planks	2,20 m <sup>2</sup>	23.71 ft <sup>2</sup>	15,7 kg
1 pallet Connect 8	56 packs	123,34 m <sup>2</sup>	1327.61 ft <sup>2</sup>	891 kg

### product specifications

Dimensions	1288 x 190 mm
Total thickness	8 mm
Bevels	0
Loc System	DuoLoc
Level of use according to European standard EN10874	23 heavy domestic use
	32 general commercial use
Residential warranty	lifetime
Commercial warranty	5 years

Warranty conditions on [www.berryalloc.com](http://www.berryalloc.com).




### composition

Surface layer	Direct laminated paper, impregnated with melamine resin.
Substrate	Moisture resistant High Density Fiberboard (HDF).
Backing	Direct laminated paper, impregnated with melamine resin.

### test results

Abrasion resistance	EN13329	AC4 (IP≥4000)
Impact resistance	EN13329	small ball : ≥ 35 mm - big ball : ≥ 750 mm
Thickness swelling	ISO24336	12% (requirement ≤ 18%)
Fire resistance	EN13501-1	Cfl-S1
Formaldehyde emission	EN717-1	E1
Slip resistance	EN13893	DS
Density	EN323	900 kg/m <sup>3</sup>
Resistance to staining	EN438	5 (groups 1+2) ; 4 (group 3)
Effect of a furniture leg	EN16581	no damage (foot type 0)
Effect of a castor chair	EN425	no damage with type W wheels
Thermal resistance in combination with underlay Excellence Plus	ISO 8302	0,08 m <sup>2</sup> K/W – Suitable for floor heating/cooling. Detailed instructions on <a href="http://www.berryalloc.com">www.berryalloc.com</a> .


lamine.



[www.berryalloc.com](http://www.berryalloc.com)

11/2023

## What is a laminate floor made of?



- ❶ An **overlay** that determines the strength and resistance of your floor
- ❷ A **decor paper** for the design
- ❸ A **high-density fibreboard (HDF)** core
- ❹ A **counterbalance** to stabilise and protect the HDF core