

# iD INSPIRATION 55-70

## TECHNICAL DATA

CERTIFICATION & CLASSIFICATION	STANDARDS	iD Inspiration 55	iD Inspiration 70
Type of floor covering	EN ISO 10582	Heterogeneous Compact Resilient Floorcovering	Heterogeneous Compact Resilient Floorcovering
Classification	EN ISO 10874	Domestic: 23 Commercial: 33 Industrial: 42	Domestic: 23 Commercial: 34 Industrial: 43
TECHNICAL CHARACTERISTICS	STANDARDS	iD Inspiration 55	iD Inspiration 70
Total thickness	EN ISO 24346	2,5 mm	2,5 mm
Wear layer thickness	EN ISO 24340	0,55	0,7
Total weight	EN ISO 23997	4000 g/m <sup>2</sup>	4000 g/m <sup>2</sup>
Wear layer binder content	EN ISO 10582	Type I	Type I
Dimensions	EN ISO 24342	Planks 16,66 x 100 cm, 22 planks/box = 3,67 m <sup>2</sup> 12,5 x 122 cm, 24 planks/box = 3,66 m <sup>2</sup> 20 x 122 cm, 15 planks/box = 3,66 m <sup>2</sup> 25 x 122 cm, 12 planks/box = 3,66 m <sup>2</sup> 25 x 150 cm, 10 planks/box = 3,75 m <sup>2</sup> Tiles 25 x 50 cm, 30 tiles/box = 3,75 m <sup>2</sup> 50 x 50 cm, 15 tiles/box = 3,75 m <sup>2</sup> 50 x 100 cm, 7 tiles/box = 3,50 m <sup>2</sup> 100 x 100 cm, 3 tiles/box = 3 m <sup>2</sup>	
Surface treatment (PUR)		Yes - TopCleanXP™	Yes - TopCleanXP™
Beveled edges		Yes	Yes
TECHNICAL PERFORMANCES	STANDARDS	iD Inspiration 55	iD Inspiration 70
Dimensional stability	EN ISO 23999	≤ 0,10 %	≤ 0,10 %
Curl resultant to heat	EN ISO 23999	≤ 2 mm	≤ 2 mm
Reaction to fire	EN 13501-1	B <sub>fl</sub> -s1 glued on wood panel and concrete	B <sub>fl</sub> -s1 glued on wood panel and concrete
Residual indentation	EN ISO 24343-1	≤ 0,05 mm	≤ 0,05 mm
Furniture leg	EN 424	No damage	No damage
Castor chair	ISO 4918 - EN 425	No damage	No damage
Impact sound reduction	EN ISO 717-2	ΔL <sub>w</sub> = 2 dB	ΔL <sub>w</sub> = 2 dB
Reduction of in-room impact noise	EN ISO 31-074	Class C (L <sub>n,e,w</sub> < 85 dB)	Class C (L <sub>n,e,w</sub> < 85 dB)
Thermal resistance	EN ISO 10456	0,02 m <sup>2</sup> K/W	0,02 m <sup>2</sup> K/W
Light fastness	EN ISO 105-B02 (method 3a)	≥ 6	≥ 6
Chemical resistance	EN ISO 26987	Not affected (0)	Not affected (0)
Slip resistance	DIN 51130 EN 13893	R9 / R10 depending on embossing μ ≥ 0,30	R9 / R10 depending on embossing μ ≥ 0,30
Electrical properties	EN 1815 EN 1081	<2 kV on concrete > 10 <sup>9</sup> Ohm	<2 kV on concrete > 10 <sup>9</sup> Ohm
Peeling resistance	EN ISO 24345	≥ 50N / 50mm	≥ 50N / 50mm
Underfloor heating		Suitable - max. 27 °C	Suitable - max. 27 °C


The above information is subject to modification for the benefit of further improvement. (07/16).

Tarkett's instructions regarding installation, cleaning and maintenance should be observed. Please contact Tarkett at the address shown for these instructions.

CUSTOMS TARIFF : 482050000000F





### Logistics Information



### Surface treatment



### General Information



THE ULTIMATE FLOORING EXPERIENCE